

Dia	Contract	Cylinder	Strength	Required	Age	Made	Tested	Design
4	117363	34	5019	3000	28	12/27/2017	1/24/2018	17490
4	117363	34A	5344	3000	28	12/27/2017	1/24/2018	17490
4	Q297	45 A	6288	3000	28	12/27/2017	1/24/2018	17566
4	Q297	45 A	6177	3000	28	12/27/2017	1/24/2018	17566
4.016	R238	1A	6959	3000	36	12/19/2017	1/24/2018	17132
4	R238	1A	7056	3000	36	12/19/2017	1/24/2018	17132
4	R238	2A	5440	3000	33	12/22/2017	1/24/2018	17132
4	R238	2A	5094	3000	33	12/22/2017	1/24/2018	17132
4	R149	4 B	3444	3000	14	1/11/2018	1/25/2018	16440
4	J363	5	6172	3000	28	12/28/2017	1/25/2018	17643
4	J363	5A	5896	3000	28	12/28/2017	1/25/2018	17643
4	117363	35	5287	3000	28	12/28/2017	1/25/2018	17490
4	117363	35 A	5380	3000	28	12/28/2017	1/25/2018	17490
4	Q298	26A	8885	3000	28	12/28/2017	1/25/2018	17075
4	Q298	26A	10055	3000	28	12/28/2017	1/25/2018	17075
4	R277	1	6015	3000	35	12/21/2017	1/25/2018	17641
4	R277	1A	6489	3000	35	12/21/2017	1/25/2018	17641
4	Q374	15B	4490	3000	5	1/20/2018	1/25/2018	15521
4	Q374	15C	4391	3000	5	1/20/2018	1/25/2018	15521
4.011	R940	2	6705	3000	28	12/29/2017	1/26/2018	17132
4.011	R940	2A	6385	3000	28	12/29/2017	1/26/2018	17132
4	R277	2	3659	3000	28	12/29/2017	1/26/2018	17641
4	R277	2A	3542	3000	28	12/29/2017	1/26/2018	17641
4	Q346	C 10	3225	3000	28	12/29/2017	1/26/2018	17458
4	Q346	C 10A	3108	3000	28	12/29/2017	1/26/2018	17458
4	107380	16 A	6053	4000	28	12/29/2017	1/26/2018	400000KX
4	107380	16 A	5910	4000	28	12/29/2017	1/26/2018	400000KX
4	Q945	17 A	7915	3500	28	12/29/2017	1/26/2018	17482
4	Q945	17 A	7582	3500	28	12/29/2017	1/26/2018	17482
4.011	Q301	17 A	7228	3000	28	12/29/2017	1/26/2018	17132
4.011	Q301	17 A	7618	3000	28	12/29/2017	1/26/2018	17132
4	117347	27	5247	3000	28	12/29/2017	1/26/2018	16370
4	117347	27A	4870	3000	28	12/29/2017	1/26/2018	16370
4.016	R136	W47	5536	4000	28	12/29/2017	1/26/2018	17602
4	R136	W47A	5738	4000	28	12/29/2017	1/26/2018	17602
4	R077	106	4710	3000	28	12/29/2017	1/26/2018	17590
4	R077	106A	5267	3000	28	12/29/2017	1/26/2018	17590
4	M950	709	6564	3000	28	12/29/2017	1/26/2018	15521
4	M950	709A	6886	3000	28	12/29/2017	1/26/2018	15521
4	P230	762	6179	3000	28	12/29/2017	1/26/2018	16170
4	P230	762A	6518	3000	28	12/29/2017	1/26/2018	16170
4	P922	133 B	2180	3000	18HR	1/25/2018	1/26/2018	18083
4	R048	G3	10269	8000	37	12/20/2017	1/26/2018	18083
4	R048	G4	10380	8000	37	12/20/2017	1/26/2018	18083
4	P922	133C	2677	3000	1	1/23/2018	1/26/2018	18083