

QPL 11 BIODEGRADABLE ASPHALT SOLVENTS

BIODEGRADABLE ASPHALT SOLVENTS

PROCEDURES

GENERAL

This evaluation procedure outlines the Department's approval process for biodegradable asphalt solvents used for extraction of bituminous mixes.

SPECIFICATIONS

None

PROCEDURES

A completed Product Evaluation Form, MSDS sheets, product data information, and a 5 gallon sample of the product being tested must be submitted to the Division of Materials and Tests.

To be placed on the Departments Qualified Products List a biodegradable solvent must meet the following requirements:

1. Flash point of 140° F or above.
2. Extract asphalt cement from a standard asphalt mix within 0.2% of the amount of asphalt used to construct the standard mix.
 - a) Using an amount of solvent not to exceed two gallons.
 - b) Using an amount of rinse water not to exceed two gallons.
- 3) Must be capable of being used by laboratory personnel using normal ventilation procedures without causing nausea.
- 4) Must rinse through filter without evidence of clumping or coagulation of the solvent.
- 5) A maximum Specific Gravity of 0.90